

a polydialkylsiloxane having acrylate and/or methacrylate groups and (ii) an organic compound free of silicon and comprising at least two reactive groups selected from of an acrylate or a methacrylate group, said adhesive tape having a 90° peel adhesion of at least 6 N/2.54 cm relative to a polyethylene film surface and said adhesive tape having a Keil test value of not more than 1 N/2.54cm.


7. An adhesive tape according to claim 1 in the form of a roll.

Remarks

The above amendment to claim 1 has been made to correct a typographic error. The amendment to claim 7 has been made to correct the multiple dependency of the initial application.

Respectfully submitted,

May 18, 2001  
Date

  
William J. Bond  
Reg. No. 32,400

Office of Intellectual Property Counsel  
3M Innovative Properties Company  
P.O. Box 33427  
St. Paul, Minnesota 55133-3427  
Telephone: (651) 736-4790  
Facsimile: (651) 736-3833

WJB:cls

**Version With Markings to Show Changes Made**

1. (Once Amended) An adhesive tape comprising a backing comprising a fibrous woven or nonwoven layer of thermoplastic polymer fibers, said backing having a first side formed of said fibrous layer with a silicone release layer and a second side of the backing opposite the first side having thereon a pressure sensitive adhesive layer, said silicone release layer comprising a cured reaction product of a curable composition comprising (i) a polydialkylsiloxane having acrylate and/or methacrylate groups and (ii) an organic compound free of silicon and comprising at least two reactive groups selected from of an acrylate ~~[[and] or]~~ or a methacrylate group, said adhesive tape having a 90° peel adhesion of at least 6 N/2.54 cm relative to a polyethylene film surface and said adhesive tape having a Keil test value of not more than 1 N/2.54cm.

7. (Once Amended) An adhesive tape according to [any of the previous claims] claim 1 in the form of a roll.